POLYMY
MEETING EXCELLENCE

TECHNICAL DATASHEET

HDPE 54B04

Analysis:

Typical Properties	Method	Value	Unit
MFI@190°C, 2.16 kg	ASTM D1238-10	3.2 – 4.8	gr/10min
MFI@190°C, 21.6 kg	ASTM D1238-10	109	gr/10min
Density	ASTM D1505-10	0.950 – 0.958	gr/ml
VOLATILES	IN HOUSE	MAX 0.05	%WT
Standard Yellow Index	DIN 6167	Min 2.5	-

POLYMY