POLYMY
MEETING EXCELLENCE

TECHNICAL DATASHEET

HDPE BL3 COMPOUND

Analysis:

Typical Properties	Method	Value	Unit
MFR (190/5kg)	ISO1133	1.2±0.3	g/10min
MFR (190/21.6)	ISO1133	23±4	g/10min
FRR21.6/5	-	19	-
Density	ISO1183	0.954±0.002	gr/ cm3
Notched impact strength(@23˚C)	ISO179/1eA	9 min	kj/m2
Swelling ratio	Internal Method	110±15	%

POLYMY